



CONTACT US

Material 70 HNBR 254067

green

print date **revision index** **revision date**
12/8/2014 4 11/6/2012

page 1 / 1

Physical properties

	required	actual	
Density DIN EN ISO 1183-1, 23 °C	1.11 ±0.02	1.11	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	70 ±5	72	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	---	5.2	MPa
Tensile strength DIN 53504, S2, 23 °C	> 12.5	16.8	MPa
Elongation at Break DIN 53504, S2, 23 °C	> 140	185	%
Compression set DIN ISO 815, B, 24 h, 125 °C, 25 %	< 20	12	%

Certificates	Country	Part	Remark	Expires	unlimited
FDA	USA		21 CFR 177.2600		<input checked="" type="checkbox"/>

Temperature-range: - 30 °C to 140 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg
FST - MCE
Material Center EUROPE
Wolfgang Becker

Phone: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

