



MATERIAL REPORT

Date: 03/21/2006

TITLE: General evaluation of Parker's Chloramine Resistant Ethylene Propylene compound EJ273-70 to ASTM D2000 M4CA710 A25 B35 EA14.

PURPOSE: To provide a general physical and chemical attribute profile of this compound.

CONCLUSION: Parker compound EJ273-70 meets all aspects of the ASTM specification with no exceptions.

Temperature: -70 to 250 (F)

Parker O-Ring Division
2360 Palumbo Drive
Lexington, Kentucky 40509
(859) 269-2351

REPORT DATA

ORIGINAL PHYSICAL PROPERTIES

	<u>SPEC.</u>	<u>PLATENS</u>
Hardness, Shore A	70±5	70
Tensile Strength, min, MPa (PSI)	10 (1450)	14.6 (2117)
Elongation at Break, min.	200	249

HEAT AGED (A25)

70 Hrs. @ 125° C

Hardness Change, pts.	±10 Max	+3
Tensile Strength Change, max	-20 Max	+9
Elongation Change, max	-40 Max	+12

Compression Set (B35)

ASTM D 395, Method B

22 Hrs. @ 125°F

% Set, Max	70 Max	15%
------------	--------	-----

Fluid Resistance (EA14)

70 Hrs. @ 100° C, Distilled Water

Volume Change, %	±5	+3
------------------	----	----

Fluid Resistance

1.00 x 2.00 x 0.040 in. Sample

70 HRS @ 50 ppm Total Residual Chlorine @ 70° C

Volume Change, %	Record	+1
------------------	--------	----

500 HRS @ 50 ppm Total Residual Chlorine @ 70° C

Volume Change, %	Record	+6
------------------	--------	----

1000 HRS @ 50 ppm Total Residual Chlorine @ 70° C

Volume Change, %	Record	+16
------------------	--------	-----

1344 HRS @ 50 ppm Total Residual Chlorine @ 70° C

Volume Change, %	Record	+33
------------------	--------	-----

“Purchaser use only. Reproduce only in full. Data pertains to items referenced only.”

“The recording of false, fictitious or fraudulent statements or entries on this report may be punishable as a felony under federal law.”