



Seals



CONTACT US

# KA183-85

Low Temperature HNBR

## TYPICAL PHYSICAL PROPERTIES

	<u>Spec.</u>	<u>Data</u>
HARDNESS, SHORE A (2-325 O-Rings)	85 ±5	88
MODULUS @ 50% ELONGATION, psi	800	846
MODULUS @ 100% ELONGATION, psi	1500	1947
ULTIMATE TENSILE STRENGTH, psi	1800	2551
ULTIMATE ELONGATION, %	100	139
SPECIFIC GRAVITY		1.36
% COMPRESSION SET, 70 HRS @ 212°F	25	18.0
TEMPERATURE RANGE		-40F - +300F.

NOTE: THESE ARE TYPICAL VALUES AND SHOULD NOT BE USED AS SPECIFICATION LIMITS

\*

**Compound KA183-85**

**Test Results**

Media	Hardness Change, Pnts.	100% Modulus Change, %	Ultimate Tensile Change, %	Elongation Change, %	Weight Change, %	Volume Change, %
Original	88	1947	2551	139		
Brayco 864 70hr @ 158F.	-5	-14	-22	-17		+8
Marsten Bently HW525 70hr @ 158F	-3	-9	-5	+1		+5
Marsten Bently HW443 70hr @158 F	+2	-5	+6	-1		+1
Methanol 70 hr @ 68-86F.	-9	-35	-30	-8		+11
Erifonn 818 70hr @ 158F	0	-5	-12	-7		+1
IRM 903, 70 hr @212F	-12	-30	-12	-2		+20
Kerosene 70 hr @ 212F	-9	-34	-34	-15		+31
Distilled Water 70 @212F	-1	0	-1	+2		+3
10% NaOH 70 hrs @ 212F	+2	-3	-11	00		+1
Baroid Petrofree drill fluid 70 hr @ 212F	-12	-30	-19	-5		+21
Heat Aging 70 hr @ 212F	-1	-7	-1	+5		0
Heat Aging 70 hr @ 250F	0	-2	+1	+3		-1
Heat Aging 70 hr @ 302F	+3	+8	-4	-12		

LL-

 70 Hrs @ Room Temperature

 168 Hrs @ 100° C

**Warning!** Failure, improper selection or improper use of the product and/systems described herein of related items can cause death, personal injury or property damage. This document and other information from Parker Hannifin Corporation, it's subsidiaries and authorized distributors provide product and/or system options for further investigation by user having technical expertise. It is important that you analyze all aspects of your application and review the information concerning the product or system in the current Product catalog. Due to the variety of operating conditions and applications for these products or systems, the user, through his own analysis and testing is solely responsible for making the final selection of the product and systems and assuring that all performance, safety and warning requirements of the application.