



# MATERIAL REPORT



REPORT NUMBER: KK2190  
DATE: 04/06/93

[CONTACT US](#)

**TITLE:** Evaluation of Parker Compound S0802-40 to ASTM D2000  
M2GE405 A19 B37 EA14 E016 F19

**PURPOSE:** To determine if S0802-40 meets the callout.

**CONCLUSION:** Compound S0802-40 meets the ASTM D2000 callout.

Recommended temperature limits: -60<sup>0</sup>F to 400<sup>0</sup>F

Recommended For

Dry heat  
Some petroleum oils  
Moderate water resistance  
Fire resistant hydraulic fluids (HFD-R and HFD-S)  
Ozone, aging, and weather resistance  
Low temperature

Not Recommended For

Ketones  
Acids  
Silicone oils  
Auto and aircraft brake fluid



**Compound Data Sheet**  
Parker O-Ring Division United States

**REPORT DATA**

Report Number: KK2190

	ASTM D2000 <b>M2GE405 A19 B37 EA14 E016 F19</b> <u>Pass / Fail Limits</u>	<b>S0802-40</b> <u>Platen Results</u>
<u>Basic Physical Properties</u>		
Hardness	35 - 45	39
Tensile Strength, Mpa (psi)	5 (725)	5.5 (802)
Elongation, %	300	448
<u>A19 ASTM D573 Heat Aging, 70 H @ 225°C</u>		
Hardness Change, pts max	+10	+3
Tensile Change, % max	-25	+2
Elongation Change, % max	-30	+7
<u>B37 Compression Set, ASTM D395, 22 HRS @ 175°C</u>		
% of Original Deflection, max	25	14
<u>E016 Fluid Immersion, ASTM #1 Oil, 70 H @ 150°C</u>		
Hardness Change, pts	0 to -10	-6
Tensile Change, % max	-30	+1
Elongation Change, % max	-30	+15
Volume Change, %	0 to +15	+4
<u>EA14 Fluid Immersion, Water PER ASTM D471, 70 H @ 150°C</u>		
Hardness Change, pts	+/- 5	0
Volume Change, %	+/- 5	-1
<u>Fluid Immersion, ASTM #3 Oil, 70 HRS @ 150°C</u>		
Volume Change, %	+ 60	+49
<u>F19 Low Temp Brittleness D2137 3 MIN @ -55°C</u>	Pass	Pass

Parker O-Ring Division  
2360 Palumbo Drive  
Lexington, Kentucky 40509  
(859) 269-2351